

Review on Solid State Thermoelectric Module and Its Use in Energy Recycling

Irshad Ali¹, M Y Yasin²

¹M.Tech. Scholar, ²Faculty member, Department of Electronics and Communication Engineering, Integral University, Lucknow, India

Abstract: Solid state thermoelectric modules are found useful in applications like cooling, heating, temperature measurement and energy harvesting. Waste heat and its management in a typical industrial process is challenging. Thermoelectric modules (TEM) are becoming popular in such applications because of their inherent characteristics like small dimensions, light weight, low cost and that they do not have any moving features. Design of thermoelectric modules for simultaneous applications of heat pump and electricity harvesting is quite a challenge for the designers. A particular vendor releases data sheet for his TEM product. This paper reviews the underlying phenomenon, modelling and applications of the TEM. In order to investigate the possibility of their industrial use, studies are conducted on three TEM's, viz., TGM-199-1.4-0.8 from Kryotherm, TG12-8L from Marlow Industries, and HZ-9 from Hi-Z Technology, Inc.

Keywords: Thermoelectric Module, Industrial Heat Management, Heat Management Systems, Electronic cooling, Energy Recycling, Energy Harvesting, Heat energy conversion.

1. INTRODUCTION

The thermoelectric module (TEM) is a solid state sensor that can be used for energy conversion. A TEM usually transforms thermal energy into electrical or vice versa [1,2]. A TEM is known as Thermo-Electric Cooler (TEC) if it pumps heat from higher temperature to a lower one, or is a Thermo-Electric Generator (TEG) if it transduces electricity for the temperature gradient across it. TEG's are already in use in the field of microelectronics as heat pump for high performance applications like LASER, CPU and other heat dissipating devices, [1]. A novel application of the TEM's is also presented

for cooling the battery and the battery compartment in hybrid vehicles [3].

TEG's can be used as efficient energy recyclers [2]. Waste heat from different heat sources in an industrial process can be converted to electricity with the help of a TEM. This application is of particular interest because (i) it cares for the energy to be otherwise going lost, and (ii) certain critical parts of the process may need deliberate cooling. Such cooling arrangements are usually expensive and maintenance intensive. TEM's are prospecting recycling devices as they are non-mechanical, flexible in size and shape, offer a low cost alternative, easily installable, do not exude pollutant gases and therefore can be a step forward for a greener environment. Furthermore, the TEM's do not need any energy input, in fact, they need only a temperature gradient at its two sides.

This study includes analysis of TEM's for their working, performance evaluation and the prospects in industrial applications.

2. STRUCTURE OF THERMO-ELECTRIC MODULE

A TEM cell is a semiconductor device which basically contains a stack of N thermocouples called TEM module. A single thermocouple is a combination of n-type and p-type semiconductor material. The n- and p-type semiconductors are connected in such a way that one end of the assembly is shorted through a metal plate, while at the other end, the semiconductors are connected to two isolated metal plates, as shown in Fig. 1. This

assembly is though in series electrically, however remains in parallel thermally [1]. The two sides are then strengthened through thin ceramic layers. The top layer, where the n- and p- semiconductor layers are shorted on a metal plate forms the cold junction (J_c), while the other end forms the hot junction (J_H), correspondingly the two sides are termed as cold and hot sides respectively. This definition of the cold and hot sides is based upon the flow of charges and the temperature difference established on the surfaces when a voltage source is applied to the isolated legs of the TEM cell, as suggested by the Peltier effect. This effect is reversible, viz., when the corresponding *cold* and *hot* surfaces are maintained at a temperature difference, a voltage will develop across the *cold* and *hot* surfaces. However, this voltage is very weak and therefore a suitable stacking is needed to collect a substantial voltage magnitude.




Fig1. Thermocouple in Thermoelectric Module

The stacked assembly is then encapsulated in a thermally conducting encasement [4]. Each semiconductor is called a pellet, and a TEM cell is composed of two dissimilar (n- and p- type semiconductor) pellets. These pellets are made by using semiconductor Bismuth Telluride (Bi_2Te_3). Different compositions of Bismuth Telluride with Antimony Telluride exhibit the well-known rectifying behaviour. In commercial TEM's, n-pellet is made by alloying (Bi_2Te_3)₉₀ with (Sb_2Te_3)₁₀, suffix indicates the percentage of alloying. Thus (Bi_2Te_3)₉₀ means 90% Bi_2Te_3 used. Similarly, the p-

pellet is made by alloying (Bi_2Te_3)₇₅ with (Sb_2Te_3)₂₅. Some High performance TEM's also use (Bi_2Te_3)₉₀ (Sb_2Te_3)₅ (Sb_2Se_3)₅ for n- pellet and (Bi_2Te_3)₇₂ (Sb_2Te_3)₂₅ p-pellet respectively [5].

The dimension of a TEM module, as shown in Fig.2, varies from vendor to vendor. Each individual vendor has its own geometrical and physical data to characterize their TEM's.




Fig. 2. Thermoelectric Module

Usually the common characteristics of TEM's are stack size (N), length of pellet (L, mm), height of the packaged module (H, mm), Area of cross section of a TEM cell (A, sq. mm), Internal Resistance of the module (R_{in}, Ω), Thermal Conductivity (K_{in} , watt per meter Kelvin) and the maximum operating temperature difference across the *hot* and *cold* sides (T_{max}). A commercial thermoelectric cooler (TEC) TB-127-1.4-1.2 from Kryotherm, is characterised by 254 (TEM cells, N), 40.0 mm (length, L), 40.0 mm (width, W), 3.6 mm (height, H), 1.6Ω (R_{in}, Ω), Seebeck Coefficient 0.0532 V/K, 70 K (ΔT_{MAX}) [1, 6].

3. PHYSICAL PHENOMEN RESPONSIBLE for TEM OPERATION

The operation of a TEM cell is quite complex. A thermoelectric process may be considered as a combination of different sub thermoelectric processes. The conversion of heat energy to electrical energy may involve any or all of the effects like heat convection, Joule heating, Seebeck effect, Peltier effect and Thomson effect [3,4]. Thomson effect is very low, so this phenomenon not discussed in this work.

Heat convection in thermoelectric module is a multistage process. Heat transfer rate depends on a physical constant λ (in watt per meter Kelvin). Thermal conductivity and geometry of a single pellet is determined with the help of λ , and the equation for heat transfer in a pellet is described as follows [1,4]

$$q = \lambda \frac{A}{L} \Delta T \quad (1)$$

Heat flow, as normal, is opposed by the material characteristic, thus giving rise to thermal resistivity. Incorporating thermal resistance, Eq.1 can be re written as

$$q = \frac{\Delta T}{2\theta} \quad (2)$$

where

$$\theta = \frac{1}{\lambda} \frac{L}{2A} \quad (3)$$

Where H is height of the pellet (mm), A (sq.mm), it's cross section area, T (K), temperature difference across *cold* and *hot* surfaces, q is heat (watt) and θ (Kelvin per watt), thermal resistance of the pair of pellets in a cell. For N TEM cells in a module, total thermal resistance of the module is given by

$$\theta_{in} = \theta / N \quad (4)$$

Seebeck effect, gives the potential difference between the two ends of a conductor, subject to the temperature gradient along it's length and can be given by [1-4]

$$U = \alpha (T_H - T_C) \quad (5)$$

U is electromotive force generated at the two ends of a single TEM cell. T_H , T_C are the hot side and cold side temperatures in Kelvin. In a TEM, two dissimilar materials are used, n-type and p-type, semiconductors, which commonly have a positive Seebeck coefficient α_{pn} in μ volt per Kelvin. Total electromotive force in a TEM can be represented as follows

$$U_{TEM} = N (\alpha_p - \alpha_n) (T_H - T_C)$$

Which can be rewritten as

$$U_{TEM} = N \alpha_{pn} (T_H - T_C) \quad (6)$$

U_{TEM} is voltage generated at two end of thermoelectric module, N is numbers of Thermocouples.

Peltier effect is another phenomenon, in which heat is pumped from hot junction to cold junction in a TEM when it carries electric current I, in ampere [1-4]. This phenomenon can be described by

$$q = I (\alpha_p - \alpha_n) (T_{HJ} - T_{CJ}) \quad (7)$$

Where q is heat (in watt) pumped from hot to cold junction. α_p and α_n are Seebeck coefficients of p- and n-type pellets (in μ volt per Kelvin).

Joule's heating Pellets of a TEM cell are electrically semi conductive, therefore the cell shows electrical resistance. Joule heating is a physical process in which heat dissipates while electric current passes through it [3,4]. If resistance of the pellet is R (Ohm) and a current I (A) passes through, total heat dissipation is

$$q = RI^2 \quad (8)$$

R of a single couple of pellet can describe as

$$R = \rho 2L/A \quad (9)$$

If TEM has N couples then, total resistance of a TEM is

$$R_{in} = R \cdot N \quad (10)$$

And hence, total heat dissipation is qN

4. ANALYSIS OF THE TEM

Different commercial TEM module vendors manufacture TEM's for energy recycling purpose

[6-8]. In the pellets of a TEM, majority carriers (holes or electrons in the corresponding pellets) move from higher temperature to lower temperature. Its reverse process is responsible for a heat pump from higher temperature to lower temperature when TEM carries electric current. Total heat ($Q = \sum q_i$) flow from hot side to cold side in a TEM is a combination of Peltier effect, Heat convection from hot junction to cold junction and Joule heating [1,4].

$$Q_H = \alpha_{pn} T_{HJ} I_L + (T_{HJ} - T_{CJ}) / \theta - I_L^2 R_{in} / 2 \quad (11)$$

$$Q_C = \alpha_{pn} T_{CJ} I_L + (T_{HJ} - T_{CJ}) / \theta + I_L^2 R_{in} / 2 \quad (12)$$

The Q_H and Q_C is the heat flow rate, from hot surface to hot junction and cold junction to cold side through upper/lower ceramic plate [3,4], Where R_{in} and θ are electrical resistance and thermal resistance of pellets respectively. Thermal convection in a thermoelectric module from hot junction to the cold junction can be given by [3,4].

$$T_{TEM} = T_{HJ} - T_{CJ} \quad (13)$$

Similarly, thermal convection from hot side to cold side can be given by

$$\Delta T = T_H - T_C \quad (14)$$

Heat convection from a junction to the corresponding surface and from surface to the ambience are correlated through junction temperature and surface temperature difference T_{TEM} and ΔT , and can be defined by

$$T_{TEM} = \beta \Delta T \quad (15)$$

β is the correlation coefficient and is the temperature difference factor between the ceramic surfaces and the actual junctions [4], ignoring the effects responsible for any temperature difference between junctions. On connecting a TEM with a load resistance R_L , I_L flows. If TEM has N thermocouples, then I_L can be given by

$$I_L = V_G / (R_{in} + R_L) \\ = \alpha_{pn} \beta \Delta T / (R_{in} + R_L) \quad (16)$$

The output power delivered by a thermocouple cell can be given by [4]

$$P_L = I_L V_L \\ = I_L (\alpha_{pn} \beta \Delta T - I_L R_{in}) \quad (17)$$

With the help of Eqs. 16 and 17, the TEM power can be given by [4]

$$P_L = (\alpha_{pn}^2 \beta^2 \Delta T^2) R_L / (R_L + R_{in})^2 \quad (18)$$

At R_{in} equal to R_L TEM will deliver maximum power [4]

$$P_{MAX} = (\alpha_{pn}^2 \beta^2 \Delta T^2) / (4 R_{in}) \quad (19)$$

Efficiency of a TEM cell is defined by the percentage (or ratio) of the transduction. Thus for a TEG, the efficiency is estimated as the ratio of the electrical energy supplied and the heat generated, and can be given by [1]

$$\eta = (I_L^2 R_{in}) / Q_H \quad (20)$$

Hence the figure of merit of a TEM module can be given by [1]

$$Z = \alpha_{pn}^2 \theta_{in} / R_{in} \quad (21)$$

5. USE of TEM IN ENERGY RECYCLING

Commercial TEM modules are manufactured for cooling/heating and energy harvesting applications. Three thermoelectric modules are selected for energy harvesting applications from different vendors. Each of the TEM can also be used as a TEC or TEG.

The module TGM-199-1.4-0.8 is a thermoelectric power generator module manufactured by Kryotherm. It has 4.1% efficiency at operating

temperature $T_c = 30$, $T_H = 200$ Celsius and closed circuit current is 2.8 A, and the open circuit voltage 4.1V. Its thermal resistance is 0.57 K/W with electrical resistance 1.46 ohm [6].

Another TEG module TG12-8L from Marlow industries, has 4.97% efficiency at operating temperature $T_c = 50$ $T_H = 230$ Celsius. While open circuit voltage is 9.43V, close circuit current is 3.38A, load resistances 3.46 Ohm and thermal resistance is 1.13 °C/W [7].

TEG from Hi-Z technology HZ-9, has 4.5% efficiency at operating temperature $T_c = 30$, $T_H = 230$ °C. Open circuit voltage 6.5V, close circuit current is 2.9A with internal resistance 1.15 Ohm [8].

Some researchers have suggested the use of TEM's in energy recycling. A solar thermoelectric harvester was suggested by Pedro Carvalhaes Dias et al., in 2015. They demonstrated the energy recycling by using the TEM module TEG241-1.0-1.2 manufactured by Everredtronics [9]. Similarly, Vladimir Leonov, et al. suggested an energy harvesting method for low power devices on human body as thermoelectric converters of the animal warmth of a man for self-powered wireless sensor nodes in 2007, and demonstrated μ W range energy harvesting with the help of TEG [2]. A novel thermal management system for electrical and hybrid vehicles was suggested by Chakib Alaoui and Ziyad M. Salameh in 2005 for temperature management in hybrid or electrical vehicles [3].

6. CONCLUSION

Thermoelectric effect is a physical phenomenon, which can be practically used for thermal heat pumping or energy harvesting. Commercial thermoelectric modules are specially designed for energy harvesting purpose. These modules are in their primary stage of growth and show efficiencies in the range 4 to 5% efficiency. Though the TEM's show low efficiency, but they may serve as a potential candidate for the future developments in the field of energy harvesting due to their inherent advantages.

7. REFERENCE

- [1] Simon Lineykin and Shmuel Ben-Yaakov, "Modeling and Analysis of Thermoelectric Modules" IEEE Transaction on Industry Applications, Vol. 43, No. 2, March/April 2007
- [2] Vladimir Leonov, et al., "Thermoelectric Converters of Human Warmth for Self-Powered Wireless Sensor Nodes", IEEE SENSORS JOURNAL, Vol. 7, No. 5, MAY 2007.
- [3] Chakib Alaoui and M. Salameh, "A Novel Thermal Management for Electric and Hybrid Vehicles" IEEE Transaction on Vehicular Technology. Vol. 54, No. 2, March 2005
- [4] Simone Dalola, Marco Ferrari, et al., "Characterization of Thermoelectric Modules for Powering Autonomous Sensors", IEEE Transaction on Instrumentation and Measurement, Vol. 58, No. 1, January 2009
- [5] Marc Hodes, "Optimal Design of Thermoelectric Refrigerators Embedded in a Thermal Resistance Network" IEEE Transaction On Components, Packaging ACKAGING and Manufacturing Technology, Vol. 2, No. 3, March 2012
- [6] Product Catalog menu, Kryotherm www.kryotherm.com
- [7] Marlow industries, TG12-8L data sheet, www.marlow.com
- [8] Hi-Z Technology, HZ-9 Datasheet, www.hi-z.com
- [9] Pedro Carvalhaes et al. All "Autonomous Multisensor System Powered by a Solar Thermoelectric Energy Harvester with Ultralow-Power Management Circuit", IEEE Transaction On Instrumentation, Vol 64, No. 11, November 2015.

BIOGRAPHIES



Irshad Ali is an M. Tech. scholar at Integral University, Lucknow, India. Currently he is working on a joint project with CSIR (Indian Institute of Toxicology & Research) Lucknow.



M Y Yasin is currently working as Asst. Professor in the Department of Electronics and Communication Engineering, Integral University, Lucknow, India. He received his Ph.D in Power minimization of electronic circuit building blocks in deep-submicron in 2014 from I.U., Lucknow. His research interest includes Low Power Circuits & system, Nano-electronics and Signal processing.