

# A REVIEW ON MECHANICAL AND THERMAL PROPERTIES OF NATURAL FIBER REINFORCED HYBRID COMPOSITES

Santhosh S <sup>1</sup>, Bhanuprakash N <sup>2</sup>

*1Mechanical Department, M.Tech student, Machine Design, SJBIT, Bengaluru, Karnataka, India*

*2Mechanical Department, Assistant Professor, SJBIT, Bengaluru, Karnataka India*

**Abstract** – Development of the composites with natural fibers and fillers as a sustainable alternative material for some engineering applications, particularly in aerospace applications and automobile applications. Natural fibers such as jute, coir, sisal, bamboo etc. Natural fibers are renewable, cheap, biodegradable, and environment friendly materials. In this paper Hybrid composites are in the form of sisal/Sic/Glass Fiber, jute/sansevieria fiber, sisal/jute fiber, jute/bamboo fiber. The mechanical and Thermal properties are discussed here, for the hybrid composites the Epoxy resin is used as binder, by adding the Filler to the Natural fibers materials we can further improve the performance of the composites. Some of the commonly used fillers are Carbon black, Calcium Carbonate, Alumina, Magnesium Hydroxide, Bone powder, Coconut Powder, Hematite powder, Tio<sub>2</sub>, Sio<sub>2</sub> Graphite etc. The filler used in this paper is the Silicon Carbide.

**Key Words; Composite material, Hybrid Composite, Sisal fiber, Jute fiber, Glass fiber, Bamboo, Silicon Carbide, Mechanical properties, Thermal properties, Epoxy.**

## 1. INTRODUCTION

A composite is a structural material that consists of two or more combined constituents that are combined at a macroscopic level and are not soluble in each other. One constituent is called reinforcing phase and the one which it is embedded is called matrix. The reinforcing phase materials may be in the form of fibers, particles or flakes. The matrix phase materials are continuous. Composites Materials are classified into Ceramic Matrix Composites (CMCs), Metal Matrix Composites (MMCs), Polymer Matrix Composites (PMCs). When the polymer resin is used as a matrix material then it is called as polymer matrix composite. Polymer composites are having properties such as low density, good thermal and electrical insulator & low cost. PMCs and MMCs are most commonly used. The polymer matrix composites consisting of polymer (e.g., epoxy, polyester) reinforced by fibers The metal Matrix

composites have a metal matrix. Metals are mainly reinforced to increase or decrease the properties. The glass is the most commonly fiber used in polymer matrix composites Because of its high strength, low cost, high chemical resistance and easy available fiber.

### 1.1 Natural Fiber

Natural fibers such as jute, coir, sisal, bamboo etc. Natural fibers are renewable, cheap, biodegradable, and environment friendly materials. Fibers from plants such as cotton, hemp, jute, sisal, pineapple, ramie, bamboo, banana, etc. as well as wood and seeds of flax are used as the reinforcement in polymer matrix composites. Their availability, low density and price as well as satisfactory mechanical properties, make them attractive reinforcement to glass, carbon and other manmade fibers. Although glass fibers possess high specific strength, their fields of application are very limited because of their inherent higher cost of production. Natural fibers such as sisal jute fibers are replacing the glass and carbon fibers due to their easy availability and cost.

### 1.2 Resin

The resins that are used in fiber reinforced composites can also be referred to as 'polymers'. All polymers exhibit an important common property in that they are composed of long chain-like molecules consisting of many simple repeating units. Man-made polymers are generally called 'synthetic resins' or simply 'resins'. Polymers can be classified under two types, 'thermoplastic' and 'thermosetting', according to the effect of heat on their properties. There are three types of resins used in the composite material industry i.e. Epoxy Resin, Polyester resin and Vinyl ester resin. Most of industrial applications of epoxy resin react with a curing cross link agent known as a hardener. Epoxy resin.

### 1.3 Filler

Filler materials are the inert materials which are used in Natural fiber reinforced composites. For modifying the chemical and physical properties of the matrix polymers to reduce material costs, improve processability and to improve product performance. Filler forms the addition strength to the mechanical and thermal properties of the composite material. In this filler silicon carbide (SiC) is one of the fillers available. The silicon carbide when used as reinforcement. It will increase the properties like young's modulus, ultimate tensile strength, tensile strength, hardness of the composite materials.

## 2 LITERATURE REVIEW

**Malla Surya Teja, et al [1]** made the Experimental Investigation of Mechanical and Thermal properties of sisal fiber reinforced composites and effect of SiC filler material. In this they exhibited that the tensile strength of composite with 10%SiC 2.53 times greater than that of composite without SiC. Thermal properties includes thermal conductivity, specific heat capacity, and thermal diffusivity.

**Braga R. A, et al [2]** The author Compare the analysis of the mechanical and thermal properties of polyester hybrid composites by jute and glass fiber. To improve mechanical properties jute was hybridized with glass fiber. The different tests are Flexural, thermal, impact, density and water absorption using hybrid composites samples. The thermal properties of the composites without glass fiber it lost more mass where temperature is a function, more percentage of glass fiber with composite lost less weight with increasing temperature. So that the composite with more percentage of glass fiber absorbs more water when composite with more jute fiber.

**Arpitha G R, et al [3]** Conclude the Mechanical properties of Epoxy Based Hybrid Composites Reinforced with Sisal/SiC/Glass Fibers. In this Sisal/SiC/Glass Fiber reinforced epoxy composites are prepared. The different samples are used for tensile, Flexural, impact and the natural fibers are added to SiC fiber, Glass fiber and their effects on tensile strength, impact strength, and flexural strength are evaluated. The sisal and glass fiber composite possess good tensile strength, sisal and glass fiber composite filled with 3% SiC possess good flexural strength and also it possess good impact strength compared other composites filled with silicon carbide. The Natural fibers with glass fibers is more with silicon carbide filler it can used in many applications which needs lower strength.

**Madhusudhan T, et al [4]** made the Comparison of Hybrid Composites with Different Filler Material. He examine the hybrid composites with 2 different fiber materials and tungsten carbide as the filler material has higher tensile strength and hardness when compared to the material with 3 fiber material & SiC as the filler material. The filled SiC with hybrid material with aramid-glass-carbon fibers showed higher strength than hybrid material with aramid and glass fiber filled with WC, this is due to resistance of the material. Hence the material is biodegradable it can be used in Making any of the household applications for underwater applications.

**Madhusudhan T, et al [5]** Mechanical Characterization of Jute and Rubber Particles Reinforced Epoxy Polymer Composites. In this tensile and flexural properties are influenced by the fiber composition than the rubber particulate. The combination of these materials in composites can be used as alternative in any synthetic fiber filled polymer composites.

**Madhusudhan T, et al [6]** Investigation on Wear Resistance Behavior of SiC Filled hybrid Composite The polymer composites with 10% sic show least wear loss in all combinations, the lowest wear loss achieved in glass rubber epoxy with 10% SiC.

**Madhusudhan T, et al [7]** Experimental Study on Wear Behavior of SiC Filled Hybrid Composites Using Taguchi Method. In This the Tested Filled Hybrid Composites With 10% SiC by weight shows a better tribological properties. By using taguchi wear test on the polymer composites the material influences the wear character, load on the material, and speed rotation of disc. Taguchi material analysis is best suited to minimize the number experiments.

**Poddar P, et al [8]** Mechanical and Thermal Properties of Short Areca nut Leaf Sheath Fiber Reinforced Polypropylene Composites. TGA, DSC and SEM Analysis. In this study the composite with 10% areca nut leaf sheath fiber possess higher mechanical properties. the mechanical properties were decreased with increasing fiber content on the other hand composite shows better fiber matrix adhesion. These new composites explore new applications and markets in packaging, automotive, aviation, shipping sectors etc.

**Mala Ashok Kumar, et al [9]** Conclude the Mechanical & Thermal properties of Epoxy Based Hybrid Composites Reinforced with Jute/Sansevieria cylindrica fibers. In this the experimental results of epoxy hybrid jute/Sc fibers are prepared with different fiber lengths where the strength increases when 1cm fiber length impregnated with epoxy

matrix. it can be observed that 2cm fiber length hybrid composites have flexural, tensile strength than 1 and 3cm. it is found that the treated hybrid composites showed higher strength than untreated composites.

**Eeday Saranya, et al [10]** In this study to examine the variation in specific heat, thermal conductivity of composite with respect to temperature, fiber and fly ash. The fly ash varies from 10 to 30% and the temperature range between 30 to 120°C. The composites with and without fly ash have been prepared with Borassus Flabellifer Reinforced Composites in polyester matrix. Borassus Flabellifer Reinforce Composites acts as a thermal insulating component and it does not require any corrosion so, the longer life is achieved and also pre-fabricated to different shapes, installation time is very less, Hence they are favorable reinforcing materials for the development of load bearing light weight materials.

**M K Gupta, et al [11]** The result shows that the hybrid composites having 50% sisal and 50% jute has higher thermal, mechanical properties & lower absorption property than sisal fiber, glass fiber hybrid composites. Further the hybrid composites can be used in field of building, packaging and automobile.

**R. Sakthivel, et al [12]** Experimental Investigation and Analysis a Mechanical properties of Hybrid Polymer Composite Plates. In this hybrid composite laminates Banana-Glass-Banana, & Glass-Banana-Glass exhibit higher mechanical properties due to chemical treatment to natural fibers, among all the hybrid fiber composites the banana reinforced epoxy hybrid composites shows higher mechanical property & also implementation of eco-friendly fibers in the automotive parts like car bumper, panels etc. by implanting these fibers we can achieve light weight & structural component in automotive parts, which in turn increases fuel efficiency.

**S.John Paul Devaseelan, et al [13]** Mechanical and Thermal properties of Hybrid Reinforcement Polymer Composite. The Natural fibers such as jute, sisal, betel nut polymer composites are more attractive due to higher specific strength & low cost. It is prepared by compression moulding method with 10, 15 wt% sisal & betel nut fiber into polymer matrix. it is seen that 10 wt% sisal & betel nut fiber the tensile and compressive properties found to be maximum. The failure morphology is examined by scanning electron microscope (SEM)

**K.T.B. Padal, et al [14]** The thermal property of epoxy polymer filled with Jute Nano fiber composite under

'Nitrogen' investigated by Thermo gravimetric Analysis (TGA) & Differential Scanning Calorimetry (DSC). Using Nano fiber improves the crystallization temperature. The physical interaction between the polymer composite and Nano fiber restrict the segmental mobility of polymer chains in vicinity of the jute Nano fibers.

**A Gowthami, et al [15]** the composite with & without silica has 100% biodegradable sisal fibers as reinforcement In the polyester matrix. The effect of silica on tensile strength and tensile modulus shows better properties comparing without silica and pure resin. the specific heat capacity increases in all samples with increase of temperature, Hence the addition of silica exhibit in both thermal and mechanical properties, the effect of fire behavior of composite which under process. In the polyester matrix. The effect of silica on tensile strength and tensile modulus shows better properties comparing without silica and pure resin. the specific heat capacity increases in all samples with increase of temperature, Hence the addition of silica exhibit in both thermal and mechanical properties, the effect of fire behavior of composite which under process.

**Subhankar Biswas, et al [16]** The Detailed Investigation on Physical, Mechanical and Thermal Properties of Jute and Bamboo Fiber Reinforced Unidirectional Epoxy Composites. The bamboo fiber shows good results in terms of tensile strength. The jute fiber reinforced epoxy Bamboo and jute fiber composites shows good flexural strength in the longitudinal and transverse distribution, the fibers distribution is not uniform in both jute and bamboo fiber epoxy reinforced composites, it is revealed that the jute fibers showed better thermal behavior compared to bamboo fiber composites.

**K. Sudha Madhuri, et al [17]** the thermal properties such as Thermo gravimetric Analysis (TGA) & Differential Scanning Calorimetry (DSC) are studied to investigate the influence of change in fiber length of untreated & treated hybrid composites. Tensile, compressive & hardness strength of glass & sisal fiber observed by alkali treatments. It is found that the treated hybrid composites show higher strength than untreated hybrid composites.

**Saravana Bavan D, et al [18]** in this the fibers are maize. From these we can conclude that it is necessary need to get good adhesion between fiber & matrix, to get a good composite material fibers should change from hydrophilic to hydrophobic characters. The maize fiber and polyester resin coated maize fiber provides a useful information on thermal degradation values of composites. Properties of natural

fibers depend on growing conditions & processing conditions. This variation makes more difficult to analyze the effects of the fibers and their interfaces on the thermal properties of the composite material, these difficulties call for development of new strategies

### 3. CONCLUSIONS

The Following may be concluded based on this review.

- The combination of the useful properties of two different materials, make them as a versatile material in the field of engineering and technology.
- The jute fiber reinforced epoxy composites showed better thermal behavior compared to other fibers reinforced epoxy composites.
- The sisal/Glass fiber without filler material had good tensile strength.
- Alkali treated Sisal and jute fiber reduces water absorption properties.
- Hybrid composites jute/E-Glass fiber has better properties than that of the jute fiber.
- The treated composites showed higher strength than untreated composites.
- Increasing filler content tends to increase the modulus & hardness but decrease tensile strength of the composite.
- Comparing Natural fibers and Glass fiber reinforced composites found that, the natural fibers were superior in Industrial applications.
- Unfilled polymer composites shows higher wear loss when compared to composites filled with Sic filler

### REFERENCES

[1] Malla Surya Teja, M V Ramana, D Sriramulu and C J Rao. Experimental Investigation of Mechanical and Thermal properties of sisal fiber reinforced composites and effect of Sic filler material. IOP Conf. Series: Materials Science and Engineering 149 (2016) 012095 doi:10.1088/1757-899X/149/1/012095.

[2] Braga R. A, Silva R. S Magalhaes Jr, P. A. A. Comparative the analysis of the mechanical and thermal properties of polyester hybrid composites by jute and glass fiber. Journal of Engineering Research and Applications, ISSN : 2248-9622, Vol. 5, Issue5, ( Part -2) May 2015, pp.113-118.

[3] G R, Sanjay M R, L. Laxman Naik. Arpitha G R Mechanical properties of Epoxy Based Hybrid Composites Reinforced with Sisal/SiC/Glass Fibers. International Journal of Engineering Research and General Science, Volume 2, Issue 5, August-September, 2014 ISSN 2091-2730.

[4] Madhusudhan T, Senthil Kumar M. Comparison of Hybrid Composites with Different Filler Material. International Journal of Engineering Research and General Science Volume 4, Issue 2, March-April, 2016, ISSN 2091-2730.

[5] Madhusudhan T , Senthil Kumar M. Mechanical Characterization of Jute and Rubber Particles Reinforced Epoxy Polymer Composites. IOSR Journal Of Pharmacy, (e)-ISSN: 2250-3013, (p)-ISSN: 2319-4219, Volume 6, Issue 12 Version. 1 (Dec 2016), PP. 23-27

[6] T. Madhusudhan, Dr. M. Senthil Kumar, Investigation On Wear Resistance Behavior Of Sic Filled hybrid Composites. International Journal of Mechanical Engineering and Technology (IJMET) Volume 8, Issue 2, February 2017, pp. 82-92 Article ID: IJMET\_08\_02\_010.

[7] Madhusudhan T and M. Senthil Kumar Experimental Study On Wear Behaviour Of Sic Filled Hybrid Composites Using Taguchi Method. International Journal of Mechanical Engineering and Technology (IJMET), Volume 8, Issue 2, February 2017, pp. 271-277 Article ID: IJMET\_08\_02\_033.

[8] Poddar P, Islam MS, Sultana S, Nur HP and Chowdhury AMS. Mechanical and Thermal Properties of Short Areca nut Leaf Sheath Fiber Reinforced Polypropylene Composites. TGA, DSC and SEM Analysis. J Material Science Eng 5: 270. doi:10.4172/2169-0022.1000270.

[9] Mala Ashok Kumar, G. Ramachandra Reddy. Mechanical & Thermal properties of Epoxy Based Hybrid Composites Reinforced with Jute/ Sansevieria cylindrica fibers. International Letters of Chemistry, Physics and Astronomy 19(2) (2014) 191-197, ISSN 2299-3843.

[10] Eeday. Saranya, Goteti. Satyanarayana, Anne Srihari Prasad. made the Experimental Investigation of Mechanical and Thermal properties of Borassus Flabellifer Reinforced Composites and Effect of Addition Of Fly Ash. International Journal of Engineering Trends and Technology (IJETT) – Volume 15 Number 8 – Sep 2014, ISSN: 2231-5381.

[11] M K Gupta, R K Srivastava. Mechanical, Thermal & water absorption properties of hybrid sisal/jute fiber reinforced polymer composite. Indian journal of Engineering & Material sciences Voil.23, August 2016, pp.231-238.



[12]R.Sakthivel, D.Rajendran. Experimental Investigation and Analysis a Mechanical properties of Hybrid Polymer Composite Plates. International Journal of Engineering Trends and Technology (IJETT) – Volume 9 Number 8 - Mar 2014.

[13]S.John Paul Devaseelan, S.Rajakumar. Mechanical and Thermal properties of Hybrid Reinforcement Polymer Composite. International journal of advances in engineering Research. IJAER2016,VOL.NO.11, Issue No. VI, June. e-ISSN: 2231-5152, P-2454-1796.

{14}K.T.B.Padal, S.Srikiran, P.Surya Nagendra. Dynamic Mechanical and Thermal properties of Jute Nano Fiber Reinforced Polymer Composite. 5th International & 26th All India Manufacturing Technology, Design and Research Conference (AIMTDR 2014) December 12th–14th, 2014, II, Guwahati, Assam, India.

[15]A.Gowthami, K.Ramanaiah, A.V.Ratna Prasad,, K.Mohana Rao , G. Sridhar Babu. Experiment on Effect of Silica on Thermal and Mechanical Properties of Sisal Fiber Reinforced Polyester Composites. J. Mater. Environ. Sci. 4 (2) (2013) 199-204 ISSN : 2028-2508.

[16] Subhankar Biswas, Sweety Shahinur, Mahbub Hasan And Qumrul Ahsan. The Detailed Investigation On Physical, Mechanical And Thermal Properties Of Jute And Bamboo Fiber Reinforced Unidirectional Epoxy Composites. Procedia Engineering 105 ( 2015 ) 933 - 939, doi: 10.1016/j.proeng.2015.05.118.

[17]K.Sudha Madhuri, Dr.H. Raghavendra Rao. An investigation of Mechanical And Thermal Properties of reinforced sisal-glass fibers epoxy hybrid composites. International Journal of Engineering Research Volume No.3 Issue No: Special 1, pp: 112-115 iSSN:2319-6890.

[18]Saravana Bavan D and Mohan Kumar G C. Thermal Properties of Maize Fiber Reinforced Unsaturated Polyester Resin Composites. Proceedings of the World Congress on Engineering 2013 Vol III, WCE 2013, July 3 - 5, 2013, London, U.K