

Study on Geopolymer Concrete Beam with Hollow Space below Neutral Axis

Sherin kurikesu¹, Abhirami s²

¹ MTech student Sree Narayana Institute of Technology Theppupara, Adoor, Kerala

²Assistant Professor, Department of Civil Engineering Sree Narayana Institute of Technology Theppupara, Adoor, Kerala

Abstract - In this paper, a detailed study was carried out on strength behaviour of flyash based geopolymer concrete with hollow space below neutral axis. Use of hollow space at and near the neutral axis will reduce the self-weight and saves concrete materials. This paper focuses on material minimization by introducing hollow space using pvc pipe in tension zone of beams. By this method, we can reduce the dead loads which contribute to seismic effect in high rise structures. Geopolymer concrete shall be produced without using any amount of ordinary Portland cement. Alkaline solution produced aluminosilicate gel that acts as the binding material for the concrete. Thus many efforts are being made to reduce the usage of opc which responsible for carbon dioxide emission. M30 grade concrete is used for ordinary and geopolymer concrete. Experimental validation was done by ANSYS software

Key Words: Fly ash, alkaline solution, opc, pvc

1. INTRODUCTION

The global warming is an environmental problem caused due to the emission of greenhouse gases, such as carbon dioxide (CO₂), to the atmosphere. As the demand for concrete increases in construction field, the demand for Portland cement also increases. Cement industry is held responsible for some of the CO₂ emissions. Thus many efforts are being made to reduce the usage of cement. The concrete just above neutral axis is less stressed whereas the concrete below the neutral axis acts as a shear transmitting media. Sustainability can be achieved by replacing the partially useful concrete, by saving concrete, which reduces the demand for material and cost. So new technology materials like geopolymers offer waste utilization and emissions reduction, in which fly ash is used as a base material instead of OPC in geopolymer concrete. Geopolymer concrete is an innovative construction material which is produced by the chemical action of inorganic molecules. Fly Ash, a by-product of coal obtained from the thermal power plant is available in plenty worldwide. Flyash is rich in silica and alumina reacted and an excellent alternative construction material to the existing plain cement concrete. In this work flyash based geopolymer is used. Flyash is a waste product generated from thermal power plant. Hence we can protect water bodies from contamination due to flyash disposal and by creating hollow space at tension zone by inserting the pvc pipe we can reduce the quantity of concrete and cost can be reduced. The electrical conduits, air

conditioning small ducts etc. also been taken through these hollow beams.

2. OBJECTIVE

The main objectives of the present study is

- The main aim of this study is to find the structural behaviour of hollow GPC beam.
- To study the flexure behaviour of hollow pcc concrete beam at different diameter pvc pipe.
- To determine the flexural strength.
- To determine the load carrying capacity of hollow concrete beams.

3. METHODOLOGY

The work methodology consist of,

- 1) Selection of grade of concrete; M30 for opc and geopolymer concrete.
- 2) Mix design of M30 grade concrete.
- 3) Creating the hollow section inside the beam with two dia 25mm pipes and 32mm pipe.
- 6) Casting, Curing and Testing
- 7) Result and discussion

4. MATERIAL USED

4.1. Flyash

Fly ash is a by-product of coal-burning power plants. Therefore, huge quantities of fly ash will be available for many years in the future. Fly ash can be used in Portland cement concrete to enhance the performance of the concrete. Flyash has been successfully used to manufacture geopolymer concrete when the silicon and aluminum oxides constituted about 80% by mass.

4.2. Alkaline solution

A combination of sodium silicate solution and sodium hydroxide (NaOH) solution can be used as the alkaline liquid.

It is recommended that the alkaline liquid is prepared at least 24 hours before use. The addition of sodium silicate solution to the sodium hydroxide solution as the alkaline activator enhanced the reaction between the source material and the solution. The concentration of sodium hydroxide solution was 16 Molar.

4.3. Coarse aggregate

Coarse aggregate used was locally available crushed angular granite metal of 20mm size .These aggregates are bound together by the cement and fine aggregate in the presence of water to form concrete.

4.4. Fine aggregate

Fine aggregate consist of natural sand or crushed stone sand. It should be hard, durable and clean and be free from organic matter .sand conforming to zone II is used.

5. MATERIAL TEST

Test results on cement, fly ash, and fine aggregate and coarse aggregate are given in table 1.

Table 1: Material property

TEST	MATERIAL USED	VALUES OBTAINED
Specific gravity	Cement (53grade)	3.16
Specific gravity	Fine aggregate (m sand)	2.56
Specific gravity	Coarse aggregate	2.96
Specific gravity	Fly ash	2.3
Water absorption	Fine aggregate	2.01%
Water absorption	Coarse Aggregate	0.326%

6. MIX DESIGN

The compressive strength and the workability of geopolymers concrete are influenced by the proportions and properties of the constituent materials .Table 3 and 4 shows the mix proportion of geopolymers concrete and OPC concrete

Table 2: Mix Design of GPC

Flyash(kg/m3)	550
Sodium silicate(kg/m3)	239.64
Sodium hydroxide(kg/m3)	95.86
Fine aggregate(kg/m3)	576.51
Coarse aggregate(kg/m3)	854.68
Extra water(l/m3)	16.5

Table 3:Mix Design Of OPC

cement(kg/m3)	394.32
Fine aggregate(kg/m3)	643.15
Coarse aggregate(kg/m3)	1246.6
water(kg/m3)	197.16
Water cement ratio(kg/m3)	0.5

7. EXPERIMENTAL SETUP

7.1 Mixing of geopolymers

In the laboratory, the fly ash and the aggregates were first mixed together for about three minutes .The alkaline solutions, sodium hydroxide solution and sodium silicate solution were prepared separately before one day of casting to get the required strength and mixed together at the time of casting. Since lot of heat is generated when sodium hydroxide pellets react with water, the sodium hydroxide solution was prepared a day earlier to casting. The alkaline solutions were added to mixed materials. The mixing of total mass was continued until the mixture become homogeneous and uniform in colour.

7.2 Curing of geopolymers

After casting the specimens, they are kept in rest period in room temperature for one day. Heat-curing substantially assists the chemical reaction that occurs in the geopolymers paste the geopolymers concrete is de-moulded and then placed in an autoclave for steam curing for 24 hours at a temperature of 60degree Celsius. The compressive strength of geopolymers concrete cubes increase with the increase in age.

8. TEST PROCEDURE

Geopolymers concrete cubes, cylinder and beam according to standard dimension were cast. cube compressive strength, cylinder split tensile strength and beam flexural strength are determined by UTM .7,14,28 days results were taken. Typical PCC beams of size 100x100x500mm were used with hollow neutral axis are made by PVC pipes of 25 mm ϕ and 32 mm ϕ. For plain geopolymers beam the neutral axis will be at the centre. The length of the pipe inside the beam neutral axis is 450mm and an anchorage length of 25mm on each side is provided for the transfer of load. The depth of neutral axis is taken as half of total length. All the beams were subjected to 2-point flexural test. Figure 1 shows the beam with pipe.



Fig 1: Beam with pipe

8. Result and Discussion

8.1. Comparison of geopolymer and conventional concrete

PARAMETRES	GPC	OPC
Compressive strength	31.01N/mm ²	30.82 N/mm ²
Tensile strength	4.46N/mm ²	4.3 N/mm ²
Flexural strength	4.85N/mm ²	4.5 N/mm ²
Poisson's ratio	0.224	0.2
Modulus of elasticity	22360Mpa	27386Mpa

From this it is observed that geopolymer concrete has same properties as that of ordinary Portland cement concrete

8.2 Comparison of solid geopolymer and geopolymer with two diameter pipe beam.

PARAMETRES	Solid GPC	25mm dia	32mm dia
Ultimate load	9.7KN	10.2KN	11.8KN
Flexural strength	4.85N/mm ²	5.1N/mm ²	5.9N/mm ²
Bending moment	1.21KNm	1.29KNm	1.47KNm
Deflection	0.135mm	0.142mm	0.164mm

8.2.1 Ultimate load carrying capacity

Fig.2 show the Ultimate load comparison of solid and hollow beams




Fig2: Comparison of load

It is observed that ultimate load carrying capacity of GPC beam with hollow space is higher than the geopolymer solid beam

8.2.2 Flexural strength

In this test, plain geopolymer concrete beam was subjected to flexure using symmetrical two point loading until failure occurs. The comparative study of flexural strength of control beams with beams having hollow near neutral axis zone is as shown in Fig. 3




Fig 3: Comparison of flexural strength

8.2.3 Deflection

The corresponding deflection of solid control beam and beam with hollow neutral axis is given in fig:4 from manual calculation. it shows that it lies within the limit as per code IS456-2000.




Fig 4: Comparison of deflection

8.3 Crack pattern

In initial stages of loading, all beams were un-cracked beam. When the applied load reached the rupture strength of the concrete on specimens, the concrete started to crack. The failure pattern in all the tested beams was observed as a flexure failure. All the beams showed the same pattern of failure.



Figure 6: Crack pattern

8.4. Concrete Reduction

Total Volume beam $V_1 = 0.1 \times 0.1 \times 0.5 = 0.005 \text{ m}^3$

Volume of pipe $V_2 = \pi \times 0.0125 \times 0.45 \times 2 = 0.00221 \text{ m}^3$

% of reduction in concrete = $(V_1 / V_2) \times 100 = 14.20\%$

Since we have assumed a small

beam, the percentage reduction is also small. When we assume this for a larger section, the percentage reduction will be larger.

8.5. Labour Reduction:

Labours are one of the major factors in construction industries. Construction labour is most disorganised in India. Direct labour cost is also a part of the prime cost. It is clearly evident from the study that the total volume saving in concrete is directly proportional to the percentage reduction in labour. Concreting works in construction industry is labour intensive. When the volume of concreting works reduce, the need for labour also get decreased simultaneously, which in turn minimise the production cost.

8.6. Cost reduction:

In current days of competition, it is necessary that a business concern should have utmost efficiency and minimum possible wastages and losses to reduce the cost of production. If the cost of input increases, then naturally, the cost of the production will go up. The inputs in construction fields include material, machines, labour and other overhead expenses. From the above conducted study we have come to a conclusion that by using geopolymer beam with hollow neutral axis, we can save significant amount of concrete without compromising the strength up to a limit. This saving in material cost is more effectively utilised when considering large depth and length of beam or in similar other works, where abnormal reduction of concrete occurs. This can be compared to a chain reaction because as the volume of concrete decreases, the material cost reduces which decreases the labour cost, which in turn minimises the construction cost.

8.7 Decrease in self weight

Dead load shall include weight of all structural and Architectural components which are permanent in nature. It

includes self-weight of the structure. The unit weight of concrete is 23 kN/m^3 . If we can reduce the volume of concrete then the self-weight of the beam also get reduced.

Weight of 1 m^3 concrete = 2300 kg

Weight of beam, $W_1 = 12 \text{ kg}$

Weight of concrete replaced by pipe, $W_2 = 0.83 \text{ kg}$

Weight of hollow beam = $W_1 - W_2 = 11.4 \text{ kg}$

Since we have assumed a small beam, the self-weight reduction is also small. When we assume this for a larger section, the weight reduction will be larger.

9. Conclusion

1. GPC has almost same properties as that of OPC.
2. From the above results, it is concluded that Hollow beam of 25mm and 32mm diameter provides higher strength and better performance and hence it is used for structure in effective way as electrical conduits, when compared to the solid conventional beam
3. Mode of failure is flexural in hollow beam of 25mm and flexure in solid and hollow (32mm)
4. It is seen that there is not much difference in the flexural strength of control beams and that of beams with low grade concrete near neutral axis zone and hollow neutral axis.
5. It can also be seen that with the increase in size of pipe replaced at neutral axis, there is no large difference in flexural strength
6. Thus in the overall study, it can be concluded that behaviour of PGC beams with hollow neutral axis behaves almost in the same manner as that of conventional concrete.

Reference

- [1] Jain Joy and Rajesh Rajeev (2014)—Effect of Reinforced Concrete Beam with Hollow Neutral Axis, International Journal for Scientific Research and Development (2014), volume 3, November.
- [2] Dr. G. Hemalatha And W. Godwin Jesudhasan (2013), —Experimental Investigation On Beams Partial Replacement Below The Neutral Axis||, International Journal Of Civil And Structural Engineering Research, Vol. 2, January.
- [3] Manikandan, Dharmar, Robertravi “Experimental study on flexural behaviour of reinforced concrete hollow core sandwich beams” International Journal of Advance Research In Science And Engineering, *IJARSE*, Vol. No.4, Special Issue (01), March 2015
- [4] Shankar H. Sanni¹, Khadiranaikar, R. B, “Performance of geopolymer concrete under severe environment conditions, International Journal Of Civil and Structural Engineering Volume 3, No 2, 2012.