International Research Journal of Engineering and Technology (IRJET) e-ISS Volume: 06 Issue: 02 | Feb 2019 www.irjet.net p-ISS

# **INVESTIGATION ON SELF HEALING CONCRETE USING EPOXY RESIN**

P. Bala Murugan<sup>1</sup>, R. Vijayalakshmi<sup>2</sup>, P. Aadhitya<sup>3</sup>

<sup>1,2</sup>Assitant Professor, Department of Civil Engineering, Nadar Saraswathi College of Engineering and Technology, TamilNadu, Theni

<sup>3</sup>PG Student, Department of Civil Engineering, Nadar Saraswathi College of Engineering and Technology, TamilNadu. Theni

\*\*\*\_\_\_\_\_\_\*

**Abstract** – Concrete is very sensitive to crack formation as wide cracks endanger the durability, repair may be required. However, these repair work raise the life cycle cost of concrete as they are labor intensive and because the structure becomes in diffuse during repair. In 1994 C. Dry was the first who proposed the intentional introduction of self healing properties in concrete. Self healing approaches offer a solution to repair these damages automatically. Healing agents are commonly encapsulated in container such as glass tubes or capsules. In this project work encapsulated epoxy resin was added to the specimen. This can be improved through the addition of microencapsulated healing agents for automatic self healing.

#### Key Words: glass capsules, epoxy resin, encapsulation...

## **1. INTRODUCTION**

It is well known that one of the weaknesses of concrete is its vulnerability to cracking. Crack may occur when concrete is in a plastic state or after it has completely hardened. Concrete may crack due to plastic shrinkage, weathering, and corrosion of reinforcement or due to applied loading. Concrete has low tensile strength and therefore concrete constructions are often combined with various type of reinforcement to resist tensile stresses. Although this is a measure to control concrete cracking, complete crack prevention is almost impossible. For example reinforcement act as local restraint against free shrinkage when concrete is in a plastic static, causing settlement cracks to form. Such occurrence may lead to more adverse problems such as spalling and even premature structural failure. Self healing capabilities are achieved by the release of healing material from the agent as a result of cracking from the onset of damage. When crack happens the agent containing self healing compounds within the concrete material break and the healing agent is released to heal the crack.

## **1.1 MATERIALS**

## **1.1.1 CEMENT**

Cement acts as a binder to join the aggregate into a solid mass. It is one of the most important constituent of concrete. Portland pozzolano cement with normal consistency was used in concrete.

#### 1.1.2 M-SAND

M-Sand is crushed aggregates produced from hard granite stone which is cubically shaped with grounded edges, washed and graded with consistency to be used as substitute of river sand because of lack of availability of river sand. Msand is preferably using for construction activities.

#### **1.1.3 COARSE AGGREGATE**

Aggregate are inert granular materials such as sand, gravel or crushed stone that along with water and Portland cement are essential ingredients in concrete. For a good concrete mix aggregates need to be clean, hard, strong particles free of absorbed chemicals or coatings of clay and other fine materials that could cause the deterioration of concrete.

# **1.1.4. WATER**

Water is the key ingredient which, when mixed with cement forms a paste that binds the aggregate together. The water causes the hardening of concrete through a process called hydration. Water also required triggering polymerization action when epoxy resin comes in contact with water so that crack can be bond together.

#### **1.1.5 EPOXY RESIN**

Epoxy resin is a usually thermosetting resin made by copolymerization of epoxies with another compound having two hydroxyl groups and used chiefly in coatings and adhesives.

## **1.1.6 GLASS CAPSULES**

Glass balls are dimensionally stable, resist corrosion and chemical absorption and can withstand high temperatures. Density varies depending upon the type glass used to manufacture the ball.

#### **1.2 EXPERIMENTAL WORK**

Concrete samples were prepared with  $M_{25}\,grade$  of concrete cube with  $150^{*}150^{*}150\,$  mm dimension.



🝸 Volume: 06 Issue: 02 | Feb 2019

www.irjet.net

# **1.2.1 ULTRA SONIC PULSE VELOCITY TEST**

Ultra sonic pulse velocity method consists of measuring the time travel of an ultra sonic pulse passing through the concrete to be tested.

SPECIME N	GRAD E	AGE ON CONCRET E	TRAVE L TIME (ms)	VELOCIT Y Km/s
cube	M <sub>25</sub>	Before crack	35.10	4.27
		On day of crack	39.30	3.82
		7 days	37.30	4.02
		28 days	36.50	4.11

# **1.2.2 COMPRESSIVE STRENGTH TEST**

Compression testing is very common testing method that is used establish the compressive force or crush resistance of a material and the ability of the material to recover after a specified compressive force is applied and even held over a defined period of time. The specimen size 150\*150\*150 are tested in compression testing machine at the completion of 7 days and 28 days.

GRADE	SPECIMEN	COMPRESSIVE 7DAYS	STRENGTH 28 DAYS
M <sub>25</sub>	Cube	24.01 N/mm <sup>2</sup>	31.32 N/mm <sup>2</sup>

# **1.3 CONCLUSION**

Based on the project result the self healing concrete with epoxy resin is functioning well based on the ultrasonic pulse velocity test and compressive strength. After prolong curing the ultrasonic pulse velocity test and compressive strength start to regain its initial reading. Capsule based encapsulation technique capable of filling cracks as well as restricting crack development. This can reduce inspection, labor and maintenance cost. Micro encapsulation self healing concrete cast at full scale have successfully demonstrated that mechanical property can be maintained and setting and hardening is unaffected by the addition of correct amount of encapsulated healing agent.

## REFERENCES

- [1] Mihashi, H., & Nishiwaki, T. 2012. Development of Engineered Self-Healing and Self Repairing Concrete-State-of-the-Art Report. Journal of Advanced Concrete Technology, 10(5): 170–184.
- [2] Zemskov, S. V., Jonkers, H. M., & Vermolen, F. J. 2012. A mathematical model for bacterial self-healing of cracks in concrete. Journal of Intelligent Material Systems and Structures, 25(1): 4–12.
- [3] British Standard. (2009). Testing Hardened Concrete. Compressive Strength of Test Specimens, BS EN 12390-3:2009.
- [4] International Concrete Repair Institute 2006 Vision 2020 A Vision for the Concrete Repair, Protection and Strengthening Industry.
- [5] Kumar V 1998 Protection of steel reinforcement for concrete— a review Corros. Rev. 16 317–58
- [6] Victor C. Li Rebust self healing concrete for sustainable infrastructure 5 April 2012