

# EXPERIMENTAL STUDY OF BAGASSE ASH AS A CEMENT REPLACING MATERIAL

Dhrmveera Singh

**M. Tech (RADHA GOVIND GROUP OF INSTITUTION, MEERUT UTTAR PRADESH)**

\*\*\*

**Abstract** – This research is therefore, conducted to examine the potential of bagasse ash as a cement replacing material bagasse ash samples are collected from Wonji's sugar factory and its chemical properties are investigated. The bagasse ash are then ground until the particles passing the 63 μm reaches about 85%, which is similar to that of Ordinary Portland Cement. Ordinary Portland Cement and Portland Pozzolana Cement are replaced by ground bagasse ash. Normal consistency and setting time of the pastes containing ordinary Portland cement and bagasse ash from 5% to 30% replacement were investigated. The compressive strength of mortars containing ordinary portland cement and pozzolana portland cement with bagasse ash from 5% to 30% replacements are also investigated. Four different concrete mixes with the bagasse ash replacing 0%, 5%, 15% and 25% of the ordinary portland cement were prepared for 35MPa concrete with water to cement ratio of 0.55 and 350kg/m<sup>3</sup> cement content. The properties of these mixes have then been assessed both at the fresh and hardened state.

**Key Words:** Bagasse, Concrete, Cement Hydration eliminate.....

## 1. INTRODUCTION

Concrete is the most commonly used construction material in the world. It is basically composed of two components: paste and aggregate. The paste contains cement and water and sometimes other cementitious and chemical admixtures, where as the aggregate contains sand and gravel or crushed stone. The paste binds the aggregates together. The aggregates are relatively inert filler materials which occupy 70% to 80% of the concrete and can therefore be expected to have influence on its properties. The proportion of these components, the paste and the aggregate is controlled by; the strength and durability of the desired concrete, the workability of the fresh concrete and the cost of the concrete.

Cement which is one of the components of concrete plays a great role, but is the most expensive and environmentally unfriendly material. Therefore requirements for economical and more environmental-friendly cementing materials have extended interest in other cementing materials that can be used as partial replacement of the normal Portland cement.

Ground granulated blast furnace slag, fly ash, silica fume, etc have been used successfully for this purpose.

## 2. LITERATURE REVIEW


Recently sugarcane bagasse ash, which is a byproduct of sugar factories found after burning sugarcane bagasse which in turn is found after the extraction of all economical sugar from sugarcane, has been tested in some parts of the world for its pozzolanic property and has been found to improve some of the properties of the paste, mortar and concrete like compressive strength and water tightness in certain replacement percentages and fineness. However, nothing has been done to check the feasibility of the bagasse ash produced in Ethiopia for this purpose

**Table 2.1 Typical composition of ordinary Portland cement**

**Chemical Name      Chemical formula      Shorthand**

Notation Weight percentage			
Tricalcium silicate	3CaO.SiO <sub>2</sub>	C3S	55
Dicalcium silicate	2CaO.SiO <sub>2</sub>	C2S	18
Tricalcium aluminate	3CaO.Al <sub>2</sub> O <sub>3</sub>	C3A	10
Tetracalcium			
aluminoferrite	4CaO.Al <sub>2</sub> O <sub>3</sub> .FeO <sub>3</sub>	C4AF	8
Calcium sulfate			
dehydrate (gypsum)	CaSO <sub>4</sub> .2H <sub>2</sub> O	CSH <sub>2</sub>	6

hydration of C3A. The hydration of C3S and C2S are shown in Eq.2.1 and Eq.2.2:



After a rapid initial reaction C3S will pass through a dormant stage which has a practical significance because it allows concrete to be placed and compacted before setting and hardening commences.



the levels found in china, which is about 800 kilograms and India about 125 kilograms per capita.

**Table 2.2 Cement production in Ethiopia in 2009.**

Plant Name	Max Capacity	2009 Capacity		
		PPC	OPC	Total
Mugher Cement	900,000	775,000	89,000	864,000
Messebo Cement	900,000	845,000		845,000
National Cement	300,000	300,000		300,000
Jemma Cement	240,000		200,000	200,000
Abyssinia Cement	150,000		100,000	100,000
Midroc Dejen	90,000		90,000	90,000
Red Fox Intl	150,000		150,000	150,000
CGOCC Cement	150,000	100,000		100,000
<b>Total</b>	<b>2,880,000</b>	<b>2,020,000</b>	<b>629,000</b>	<b>2,649,000</b>

Despite the rising supply, the cement demand in the country has been increasing even more than the supply due to large-scale public sector infrastructure projects (roads, power plants) and private sector construction activity for residential housing, industry, and real-estate developments. Table 2.3 below shows the

consumption estimates and the growth rate of cement in Ethiopia:

**Table 2.3 Cement consumption in Ethiopia (million)**

Year (G.C)	Consumption Estimate (million tons)	Growth rate (%)
1996	0.67	.....
1997	0.77	14.9
1998	0.75	- 2.60
1999	0.74	- 1.30
2000	0.82	10.80
2001	0.82	0.00
2002	0.97	18.30
2003	1.04	7.20
2004	1.17	12.50
2005	1.81	54.70
2006	2.00	10.50
2007	2.50	25.00
2008	3.20	27.00

### 3. MATERIALS AND METHODS

#### 3.1 MATERIALS

Following materials are used in this experiment -

- Cement
- Fine aggregate
- Coarse Aggregate
- Water
- Bagasse Ash

#### 3.2 METHODS

##### WORKABILITY

The workability of cement concrete is tested as per using standard sizes of Slump Moulds as per IS: 1199 - 1999.

## COMPRESSIVE STRENGTH

For find out compressive strength of cement concrete we casted steel cube mould of size of 150mm\*150mm\*150mm. After 24 hour casting of cube removing the mould and allowed for curing in a curing tank for a period of 28 days. After 7days & 28 days of curing of cube we tested the cube on Universal Testing Machine. The test procedure is used as per IS: 516-1979.

## 4. CONCLUSIONS

The use of bagasse ash as a cement replacing material in concrete production is studied and after the research work is done, the following conclusions are made:

1. The chemical composition test reveals that the bagasse ash from Wonji's sugar factory can be assigned as class N pozzolana, as prescribed by ASTM C 618, i.e.  $\text{SiO}_2 + \text{Al}_2\text{O}_3 + \text{Fe}_2\text{O}_3$  is greater than 70%.
2. Higher replacements of cement by bagasse ash resulted in higher normal consistency (implying higher water demand for certain workability) and longer setting time.
3. The workability of mortar and concrete containing bagasse ash decreases slightly as the bagasse ash content increases which is due to the higher water demand of bagasse ash.
4. The investigation of this thesis has revealed that replacement of ordinary Portland cement by bagasse ash from 5% to 10% results in a better compressive strength than that of the control mortar with 100% ordinary Portland cement. And the compressive strength decreases as the bagasse ash replacement increases over 10%.

Moreover, all of the OPC- BA blended mortars satisfy the ASTM C 618 minimum pozzolanic activity index requirement i.e. 75%.

## REFERENCES

1. Cook D.J., Pama R.P., Weerasingle H.L.S.D. "Coir fibre reinforced cement as a low cost roofing material" Build Environ 1978;13(3):193-8.
2. Perez-Pena .M and Mobasher .B, "Mechanical properties of fiber reinforced lightweight concrete composites ". Cement and Concrete Research, Vol. 24, No. 6, pp. 1121-1132, 1994

3. Brandt AM. "Cement-based composites: materials, mechanical properties and performance". London: E&FN Spon; 1995. p.470

4. Nakamura H, Mihashi H. "Evaluation of tension softening properties of fiber reinforced cementitious composites." Fracture Mechanics of Concrete Structures 1998; I:499e510.

5. Mirza F.A., Soroushiannnd P. "Effects of alkali-resistant glass fiber reinforcement on crack and temperature resistance of lightweight concrete." Cement and Concrete Composites 2002;24(2):223-7.

## BIOGRAPHIES



Dharmveera Singh