

Research Review on Multi-Objective Optimization of Machining Parameters by using Response Surface Methodology EN-31 Alloy Steel Metal

Ravindra Kumar Verma¹, Purushottam Kumar Sahu², Jagdish Saini³

¹BM College of Technology RGPV Bhopal

²HOD Mechanical Engineering department

³ Professor, Dept. of Mechanical Engineering, BM College of technology, Madhya Pradesh, India

Abstract - In this paper deals with the literature review of various factors that affect the turning operation. Traditionally, Turning is done manually on lathe machine which require constant supervision of operator on lathe machine, or on automated lathe machine which does not require continuous supervision. Such type of automation is called computer numerical control or CNC. In this paper various process parameters like speed, depth of cut, feed, nose radius, etc. are studied. This study will help us in understanding, which parameters is significant parameter for Surface Roughness, Material Removal Rate, Feed Rate, Machining Time, Tangential Force, Tool Life, etc. After careful study of a spread of research papers on this subject, it had been decided that several input also because the output parameters would be considered including feed, depth of cut and cutting speed were taken because the input parameters whereas Material Removal Rate (MRR) and surface finish were taken because the output parameters. From the results of the research papers, it had been concluded that feed, depth of cut and cutting speed might be chosen as input parameters whereas MRR and surface finish would be the output parameters.

The response model is verified based on the evaluation capability. Later, multi-objective optimization using the response surface methodology has been used to reduce the Machining Time and Maximize Material Remover Rate, resulting in a total desirability of 0.9931

Key Words: Taguchi method, S/N ratio, RSM, Optimization, Orthogonal array, ANNOVA.

1. INTRODUCTION

Turning is one in every of the foremost unremarkably used metal removal operations in business due to its ability to get rid of material quicker giving fairly sensible surface quality. It's utilized in a range of producing industries together with region and automatic sectors. Throughout turning method we tend to expect highest metal removal rate so as to attain highest production at reduced time and value. Metals from the outer edge of a cylindrical l work piece square measure removed and also the volume of metal removed per unit time is thought as metal removal rate or MRR. A turning machine or shaper, work piece, fixture, and cutter square measure needed throughout the turning operation.

The work piece may be a piece of re-shaped metal that's secured to the fixture that it is hooked up to the turning machine, and allowed to rotate at high speeds. The cutter is usually a single-point cutter that's additionally secured within the machine. The cutter feeds into the rotating work piece and cuts away material within the kind of little chips to form the will form.

It is also necessary to optimize the input process parameters in order to improve the productivity, reduce operational cost and quality of the machined component. This paper also estimates the contribution and significance of process parameters via Analysis of Variance (ANOVA) technique. This paper deals with the optimization of the machining parameters by using Taguchi's robust optimization technique and to develop prediction model to select the best combination of input parameters towards maximum material removal rate for EN-31 materials. Taguchi's L9 orthogonal array has been designed with three parameters in three factors. The S/N magnitude relation is been calculated to structure the analysis of variance table and study the performance characteristics in turning method. ANOVA analysis provides the contribution proportion of each method parameter. Notation of orthogonal array is La wherever "L" is symbol for orthogonal array, "a" stands for the number of experiments required for this array. Taguchi methods (For the data analysis, Statistical Techniques of ANOVA was used) are performed find out significant parameters. it was concluded that feed, depth of cut and cutting speed could be chosen as input parameters whereas MRR and machining time would be the output parameters.

The major shaping machine machine operations embrace turning, facing, threading, and boring. However, with attachments, or any other acceptable means of improvisation, many other operations can be possible with lathe machines. These operations primarily involve surface generation with single purpose cutting tools.

The quality of the generated surfaces is a crucial considers industrial production or manufacture of machined components. It is a function of the machining condition, and cutting tool and work-piece material and geometry.

Turning method, which is of interest in this work, involves externally cylindrical surface generation.

1.1 OVERVIEW OF MACHINING PROCESSES

Metals are formed into completely different usable forms through numerous processes during which no chip formation takes place. In these processes, the metal is formed under the action of heat, pressure or each. This class includes operations like shaping, drawing, spinning, rolling, extruding etc. A few of the important machining processes falling in this category are turning, milling, drilling, shaping, planning, broaching etc. Turning is that the most generally used among all the cutting processes. The increasing demands for turning operations is attaining new dimensions at the present, in which the growing competition needs all the efforts to be directed towards the economical manufacture of machined parts.

2. REVIEWS OF RELATED LITERATURE

Dileep Kumar C., et al (2014) [4] focused on an experimental study to find the effects of cutting parameters on surface finish and optimize them for better surface finish and high Material Removal Rate (MRR) during turning of Ti-6Al-4V. Uncoated WC/Co inserts are used for the machining purpose. A combined Taguchi method and Grey Relational Analysis (GRA) is used for the optimization. Analysis of Variance (ANOVA) is employed to find out contribution of each parameter. Four parameters are chosen as process variables: cutting speed, feed, depth of cut and nose radius each at three levels. The experiment plan is designed using Taguchi's L9 Orthogonal Array (OA). The results show that feed rate and nose radius are the most important parameters that affect the surface finish. A model is also developed separately for both surface finish and MRR using multiple regression analysis.

Basim A. K. et al (2015) [6] have experimented to develop a predictive model for surface roughness and temperature in turning operation of AISI 1020 mild steel using cemented carbide in a dry condition using the Response Surface Method (RSM). In this work, the input cutting parameters are cutting speed, feed rate and depth of cut. From the experiment it is found that Feed rate is the most significant factor on surface roughness.

Mohan S., Dharmpal D., et al (2010) [12] have investigated the robust design technique to minimize the variance of the response and orthogonal arrays. Experiments are designed and conducted based on Taguchi's L9 Orthogonal array design. This study discusses the use of Taguchi Parameter Design for optimizing surface roughness generated by a CNC turning operation.

J.B.Shaikh, J.S.Sidhu, et al (2014) [14] have determined the influence of lubricant on surface roughness and material removal rate (MRR) by using CNC LATHE

Machine with AISI D2 steel as a work material and TiAlN coated carbide tool as a tool material. Different lubricant used on this experiment are Cotton seed oil, Servo cut and soya bean oil and machining parameters are cutting speed, feed rate and depth of cut. Experiments are designed and conducted based on Taguchi's L9 Orthogonal array design. After the Analysis of Variance was made, it is found that feed rate, Cotton seed oil, Servo cut and soya bean oil has got the greater influence on surface roughness.

M. Gupta, et al (2015) [15] they investigated the machinability of unidirectional glass fiber reinforced plastics (UD-GFRP) composite while carrying out turning operation. The parameters used to investigate their effect on output responses are tool nose radius, tool rake angle, feed rate, cutting speed, cutting environment (dry, wet and cooled) and depth of cut. Experiment are designed and conducted based on Taguchi's L18 Orthogonal array design.

S. A. Rizvi, et al (2015) [16] have analyzed that an effort was made to optimize the cutting parameters to achieve better surface finish and to identify the most effective parameter for cost evolution during turning by using CNC LATHE MACHINE with IS 2062 steel rods (35 mm diameter) as a work material and Chemical Vapour Deposition (CVD) coated carbide inserts as a tool material. In this work, the input parameters are cutting speed, Feed Rate and Depth of cut.

S. Sahu, B.B.Choudhury(2015) [17] have analyzed that the performance of multi-layer TiN coated tool in machining of hardened steel (AISI 4340 steel) as a work material under high speed turning uncoated tool use. In this work, the input parameters are cutting speed, Feed Rate and Depth of cut. Experiment are designed and conducted based on Taguchi's L16 Orthogonal Array design. From the Taguchi analysis it has been found that the feed is playing as a main parameter for reducing surface roughness, whereas depth of cut is having significant effect on the surface roughness.

T. Rajasekaran, K. Palanikumar, et al (2013) [19] during this work, the input parameter area unit cutting speed, feed rate and depth of cut in turning by victimisation typical shaper (MakeNAGMATI, INDIA). Experiment are designed and conducted based on Taguchi's L9 Orthogonal Array design. From the Taguchi analysis it has been found that primarily feed rate and secondarily cutting speed has got the greater influence on surface roughness.

Yusuf S., et al (2005) [20] have determined surface roughness model response surface methodology (RSM) with low-carbon steel as a piece material and TiN coated inorganic compound as a tool material. In this work, cutting parameters area unit cutting speed, feed rate and depth of cut from the experiment it's

Ilhan A., et al (2011) [21] have investigate the effect of cutting speed, feed rate and depth of cut using AISI 4140 (51 HRC) steel as a work material and Al₂O₃ and TiC coated carbide as a tool material. Experiment are designed and conducted based on Taguchi's L9 Orthogonal Array design. Through the experiment it is found that Feed rate is the most significant factor on surface roughness.

Satyanarayana K., et al (2015) [22] have determined that effect of process parameters on performance characteristics in finish hard turning of MDN350 steel using cemented carbide tool. In thiswork, the input cutting parameters are cutting speed, feed rateand depth of cut. Experiment are designed and conducted based on Taguchi's L9 Orthogonal Array design. From the experiment it is found that Feedand Cutting speed are the most significant factor on surface roughness and Cutting Force respectively.

Ashvin J. M., et al (2013) [23] have investigated the effect of turning parameters such as cutting speed, feed rate, tool nose radius and depth of cut on surface roughness with AISI 410 steel as a work material and ceramic as a tool material using Response Surface Methodology (RSM).In this study Feed rate is the mostsignificant factor on surface roughness.

2.1 CONCLUSION OF RESEARCH REVIEW

The above literature review clearly shows that most of the research has taken the speed of the input parameters, feed and depth of cut, while some have explored its effect on performance parameters like MRR, surface roughness, cutting nose, Radius, smooth ness etc. Forces, tool wear and tool life.

Surface roughness: - The most important factor is the depth of feed and cut followed by speed. Also the lubricant and the radius of the nose have a significant effect in achieving a better effect

Rate of material removal: important factor after duplicate speed of cut and feed.

Tool wear: - The depth of feed and cut is the major factor after speed.

The feed force: - The depth of feed and cut is the important factor after speed and tool material.

The thrust force: - Feed and cut off depth is the major factor followed by speed and equipment content.

Tangential force: - The depth of cut and feed is the important factor after the speed.

Factor tool life: - Speed and feed are important factors followed by the depth of cut.

Nowadays the customer demands the best quality product. The above factors must be considered in order to achieve such demands.

REFERANCES

- [1] Upinder Kumar Yadav, Deepak Narang&Pankaj Sharma Attri, "Experimental investigation and Optimization of machine parameters for surfaceroughness in CNC turning by Taguchi method", International Journal of Engineering Research and Application", vol. 2, Issue 4, pp 2060-2065. , 2012
- [2] Harish Kumar, Mohd. Abbas, Dr.Aas Mohammad &HasanZakirJafri, "Optimization of cutting parameters in CNC Turning", Internation]ournal of Engineering Research and Applications", vol. 3, Issue 3, pp. 331-334, 2013.
- [3] BalaRaju. J, Anup Kumar. J. Dayal Saran. P, C.S. Krishna Prasad Rao, -Application of Taguchi Technique for Identifying Optimum Surface Roughness in CNC end Milling Process, International Journal of Engineering Trends and Technology, Volume 2, pp. 103 - 110, March 2015.
- [4] J.B.Shaikh, J.S.Sidhu., -Experimental Investigation and Optimization of Process Parameters in Turning of AISI D2 Steel using Different Lubricant||, International Journal of Engine
- [5] Ramyasree Keerthi, Anitha Lakshmi Akkireddy., -To Investigate the Effect of Process Parameters on SurfaceRoughness of AISI 1045 Steel in Dry Machining with CBN Cutting Tool Using ANOVA||, Vol. 25, No.1, July 2015.
- [6] Basim A. Khidhir , Waleed Al- Oqaiel, PshtwanMuhammed Kareem., Prediction Models by Response Surface Methodology for Turning Operation, American Journal of Modeling and Optimization, Vol. 3, No.1, pp. 1-6, 2015ering and Advanced Technology, Vol. 3, Issue 5, June 2014
- [7] Krishankant, JatinTaneja, MohitBector and Rajesh Kumar, "Application of taguchi method for optimizing turning process by the effects of machining parameters," International journal of engineering and advanced technology, vol. 2, no. 1, October 2012.
- [8] U. D. Gulhane, A.B. Dixit, P.V. Bane and G.S. Salvi, "Optimization of process parameters for 316L stainless steel using taguchi method and anova," International journal of mechanical engineering and technology, vol. 3, no. 2, pp. 67-72, May-August2012.
- [9] L B Abhang, and M Hameedullah, "Optimization of machining parameters in steel turning operation by taguchi method," International conference on modeling optimization and computing, Procedia Engineering 38, 2012, pp. 40-48.