

# Chemical Stabilization of Clayey Soil Using Blend of Calcium Carbide Residue and Coconut Shell Ash

SUNNY KUMAR<sup>1</sup>, ER. ANOOP SHARMA<sup>2</sup>

<sup>1</sup>PG Student, Department of Civil Engineering, S.S.C.E.T, Badhani

<sup>2</sup> ASSISTANT PROFESSOR, Department of Civil Engineering, S.S.C.E.T, Badhani

-----  
\*\*\*  
-----

## Abstract

Calcium rich and silica rich waste materials are abundantly available in many countries. These wastes ended in a waste dump there by polluting environment and endangering the lives of the people living within the vicinity. Calcium carbide residue CCR and coconut shell ash CSA are such wastes produce as result of industrial and agricultural activities. Utilizing these wastes for stabilization purposes may result in providing a product with adequate strength for construction purposes. In this research, CCR and CSA were employed in stabilizing CI, CSA was fixed at 20% in CI respectively using index properties tests and then CCR was varied ( i.e. 0.5, 1.0 and 1.5% ). Standard proctor test results showed general decrease in MDD values and increase in OMC values which may be obvious as the specific gravity of the additives is less than that of the soil. UCS results indicated a tremendous improvement in the strength of the soil with the improvement of up to 1.59 times the strength of the virgin soils at 7 days curing period and CBR results Showed Enhancement in the strength of the soil with the improvement of up to 2.1 times the strength of the virgin soils at 7 days curing period with combination of S+1.5%CCR+20%CSA respectively. Hence CCR and CSA can be employed for expansive soil stabilization subject to further researches.

**Keywords:** Clay soil, Calcium carbide, Black cotton soil, Standard proctor, CBR Test, Unconfined strength test (UCS)

## I. INTRODUCTION

There are various types of soils which show volume changes due to change in the moisture content. This causes major damage to property constructed on it. These soils contain minerals such as montmorillonite that are capable of absorbing water. When they absorb water their volume increases. One of the biggest necessities in the developing countries is to provide proper roadway network by conventional method. Hence it is necessary to go for suitable method of low cost road construction followed by a process of stage development of the roads, to meet the growing needs of road traffic.

Good quality of subgrade soil is preferable for durable road but not always available for highway construction. The highway engineers designing a road pavement face weak or unsuitable subgrade. In this situation improvement in the properties of the existing soil by addition of some other materials can be adopted which is otherwise known as "soil stabilization". Soil Stabilization:

Soil stabilization means the improvement of the stability or bearing capacity of a poor soil by the use of compaction; proportioning and the addition of suitable stabilizers or admixtures. Soil stabilization includes chemical, mechanical, physico-chemical methods to make the soil stabilized. This process basically involve excavation of soil, this is an ideal technique for improving of soil in shallow depth, as in pavements. Stabilization method may be categorized as two main types: (a) improvement of soil properties of existing soil without using any type of admixture; and (b) improve the properties with the admixtures.

The commonly used admixtures for the stabilization of clayey soil have been reported in the literature are cement, lime, flyash, rice husk ash, furnace slag or in the combination of more than one admixture. Fly ash, rice husk ash and furnace slag are added due to the abundance of pozzolanic materials ( $\text{SiO}_2$  and  $\text{Al}_2\text{O}_3$ )

**II. MATERIALS**

**A. Soil**

Soil is taken from for this exploration work. The measure of soil is taken around 150 kg of locally accessible clayey soil (CI) was gathered and air dried in open ranges. The superfluous materials like rocks and vegetative matter were expel physically from soil. The irregularities are available in soil are additionally broken with the assistance of wooden sledge and after that sieved through 4.75 mm strainer to concentrate rock part. By then the earth illustration was oven dried for 24 hours at 100 °C before it was mixed with Calcium Carbide and Ground Granulated Blast Furnace Slag using it for trials. The properties of soil used are given below in table 1.

Table No. 1 Properties of soil:

S.NO.	PROPERTIES	RESULTS
1.	Liquid Limit	47 %
2.	Plastic Limit	21.11 %
3.	Plasticity Index	25.89 %
4.	Optimum Moisture Content	17.5 %
5.	Maximum Dry Density	16.2 kN/m <sup>3</sup>
6.	Specific Gravity	2.67
7.	Indian Soil Classification	CI
8.	California ratio test	2.2 %
9.	Unconfined compression strength	240.05 kN/m <sup>2</sup>

**B. Calcium Carbide Residue:**

The Calcium Carbide Residue is used in this research was taken from Locally market.

Table No. 2Chemical composition of Calcium Carbide Residue

S. No	Name of constituent	Percentage
1	SiO <sub>2</sub>	6.49
2	Al <sub>2</sub> O <sub>3</sub> + Fe <sub>2</sub> O <sub>3</sub>	5.80
3	Calcium Oxide (CaO)	70.78
4	Magnesium oxide (MgO)	0.69
5	SO <sub>3</sub>	0.66

### C. Coconut shell Ash

The material Coconut shell ash was taken local market.

Table No. 3 chemical composition of Coconut shell ash

S. No	Name of constituent	Percentage
1	SiO <sub>2</sub> chemical composition of Coconut shell ash	37.97
2	Al <sub>2</sub> O <sub>3</sub> + Fe <sub>2</sub> O <sub>3</sub>	39.60
3	Calcium Oxide (CaO)	4.98
4	Magnesium oxide (MgO)	1.89
5	SO <sub>3</sub>	0.71
6	Na <sub>2</sub> O	0.95
7	P <sub>2</sub> O <sub>5</sub>	0.32

### III. SOIL PREPARE & EXPERIMENT

The soil take up in the proposed study was gathered from local area. Right off the bat the soil knots were broken with the assistance of a wooden hammer and after that air dried. At that point soil was gone through from sifter 4.75 mm and after that gathered in packs. The amount of soil required is then oven dried at 105°C for 1 day.

#### A. LABORATORY TESTS

Various tests that were performed in the laboratory to attain the desired objectives

1. Pycnometer test (Specific gravity).
2. Casagrande's test (Liquid limit).
3. Thread test (Plastic limit).
4. Modified proctor test (OMC and MDD)
5. CBR test.
6. UCS test

#### B. MIX PROPORTIONS USED

In present work the ratio of Calcium Carbide Residue utilized was 1.0, 1.5 and 2.0% and Coconut hell Ash was 15, 20 and 25%.

Here, S=Soil, CSA = Coconut shell Ash & CCR= Calcium Carbide Residue.


#### IV. RESULTS AND DISCUSSION

##### 1. STANDARD PROCTOR TEST:

Table No. 1 MDD and OMC for soil- CSA- Calcium Carbide mix

S. No.	Proportion Soil : CSA: Calcium Carbide	MDD (kN/m <sup>3</sup> )	OMC (%)
1.	100:0:0	16.20	17
2	79.5:20:0.5	16.75	18.6
3	79:20:1.0	17.40	19.3
4	78.5:20:1.5	17.06	18.8

Graph No. 1 Graphs representing the curves that are obtained from standard proctor test for soil - Coconut Shell Ash - Calcium Carbide mixture




##### A. Unconfined Compression Strength Test

Table No. 2 Results of UCS of Coconut shell Ash and Calcium carbide

Clayey Soil :CSA: CC	Curing Period (Days)	UCS (kN/m <sup>2</sup> )
100 : 00	7	240.05
79.5:20:0.5	7	321.43
79:20:1.0	7	357.61
78.5:20:1.5	7	381.73

Graph No. 2 UCS Value of Clayey soil of Coconut shell Ash and calcium carbide




**B. California Bearing Ratio Tests**

Table No. 3 Results of CBR of Rice Husk Ash and Nylon Fibre Mix with Soil

CS: CSA: CC	CBR (%)
100:00:00	2.2
79.5:20:0.5	4.1
79:20:1.0	4.3
78.5:20:1.5	4.6

Graph No. 3 CBR Percentages of Clayey soil, Rice Husk Ash and Nylon Fibre



## DISCUSSIONS

### MODIFIED PROCTOR TEST:

- With Coconut Shell Ash kept constant at 20% MDD decreases with an addition of Calcium Carbide content in soil and Coconut Shell Ash mix. The reason behind of such behaviour is Coconut Shell Ash is lighter in weight and it has high water absorption properties because of presence of calcium oxide and hence OMC increases with increase of Coconut Shell Ash content.

### CBR TEST:

- The CBR value of virgin soil is 2.2 and it increase to 2.1 times when Coconut Shell Ash 20% and Calcium Carbide 1.5% is added to virgin soil. This enhancement in CBR may be because of the gradual formation of hydration compounds in the soil due to the reaction between the stabilizers and the essentials particle present in the soil.

### UCS TEST:

- The UCS value of virgin soil also improves considerably with expansion of Coconut Shell Ash 20% and Calcium Carbide 1.5%. The value increases from 240.05kN/m<sup>2</sup> to 381.73kN/m<sup>2</sup> with addition of Coconut Shell Ash and Calcium Carbide.
- The reason behind of this when Coconut Shell Ash and Calcium Carbide comes in contact with water, pozzolanic reactions takes place during the curing period.

## V. CONCLUSION

1. The C.B.R value increases with increase of Calcium Carbide along with fixed quantity of Coconut Shell Ash. It increased 2.1 times from the untreated soil.
2. The optimum value of Coconut Shell Ash and Calcium Carbide required for soil stabilization is 20% and 1.5% by weight of soil respectively.
3. Unconfined compressive strength increases with increase of quantity of Calcium Carbide and with fixed quantity of Coconut Shell Ash. The value of Unconfined compressive strength is increased 1.59 times from the untreated soil.

## REFERENCES

1. **Balaraba wade isah and S. Mary rebekahsharmila (2015)** "Soil Stabilization Using Calcium Carbide Residue and Coconut Shell Ash" Journal of Basic and Applied Engineering Research Print ISSN: 2350-0077; Online ISSN: 2350-0255; Volume 2, Number 12; April-June, 2015 pp. 1039-1044.
2. **F. Okonta, Innocent kafodya (2018)** "Effects of natural fiber inclusions and pre-compression on the strength properties of lime-fly ash stabilised soil" Elsevier (Construction and building materials) Volume 170, 10 May 2018, Pages 737-746
3. **P.B Madakson, D.S Yawas and A. Apasi (2012)** "Characterization of Coconut Shell Ash for Potential Utilization in Metal Matrix Composites for Automotive Applications". International Journal of Engineering Science and Technology (IJEST) ISSN: 0975-5462 Vol. 4 No.03 March 2012.
4. **Utsev, J.T Taku, J.K (2012)** "Coconut Shell Ash As Partial Replacement of Ordinary Portland Cement In Concrete Production". International journal of scientific & technology research volume 1, issue 8, September 2012 ISSN: 2277-8616
5. **B.R. Phanikumar, Ravideep Singla (2016)** "Swell-consolidation characteristics of fibre reinforced expansive soils"

6. **Dr. Siddhartha Rokade, Rakesh Kumar, Dr. P.K. Jain(2017)** “Effect of Inclusion of Fly-Ash and Nylon Fiber on Strength Characteristics of Black Cotton Soil”. EJGE Vol. 22 [2017].
7. **Hesham A. H. Ismaiel (2013)** “Cement Kiln Dust Chemical Stabilization of Expansive Soil Exposed at El-Kawther Quarter, Sohag Region, Egypt”.
8. **M.Heeralal, G.V. Praveen(2011)** “ A study on effect of fiber on cement kiln dust stabilized soil”. JERS/Vol. II/ Issue IV/October-December, 2011/173-177
9. **M.K. Rahman, S. Rehman & O.S.B. Al-Amoudi(2011)** “Literature review on cement kiln dust usage in soil and waste stabilization and experimental investigation”.
10. **Kameshwar Rao Tallapragada, Anuj Kumar Sharma, TarulataMeshram(2009)** “laboratory investigation of use of synthetic fibers to minimize swell in expansive subgrades”. IGC 2009, Guntur, INDIA
11. **Pallavi, Pradeep Tiwari, Dr P D Poorey(2016)** “Stabilization of Black Cotton Soil using Fly Ash and Nylon Fibre”. IRJET Volume: 03 Issue: 11 | Nov -2016
12. **Indian Standard Code IS 2720-16, IS 2720-10.**